



Tygon[®] XLCOMP 60 IB

High Performance Tubing for Resin Injection & Transfer Molding for Composites Parts

Tygon[®] XLCOMP 60 IB has been specifically designed to meet the severe and demanding composites manufacturing field and handling resin media. Whereas in an effort to increase final part quality, production-efficiency and velocity of those processes, the technical requirements for resin injection (RTM) or infusion are increasingly becoming the key-parameters for the OEM.

Temperature and Pressure

To assure proper resin transfer, Tygon XLCOMP 60 IB tubing is designed to withstand high temperatures up to 200°C and injection pressure up to 8,5 bars. Made of silicone material and approved by aircraft manufacturers, this specific formulation is the ideal choice resin conveyance.

Transparent and Flexible

The tubing transparency permits visual observation of the resin being conveyed, enabling the user/operator to carefully monitor the injection process. Also, the flexibility allows for easy installation on every machine.

Industry Compliance

Manufactured in an EN9100 site, this tubing is specifically designed for the demanding aerospace industry and can be used in many other applications such as automotive and marine industries



Features and Benefits

- High temperature resistance
- High pressure resistance
- Compatible with injection resin (RTM6 in particular)
- Excellent tear resistance
- Designed specifically for resin injection
- Smooth inner bore
- Transparent
- Excellent bend radius

Compliance

- Manufactured in EN9100 certified plant
- Airbus qualified material

Manifold

- Ease of installation
- Ready to connect
- Safe connections

Tygon® XLCOMP 60 IB

ID		OD		Hardness (Shore A)	Maximum Recommended Service Pressure at 23°C*		Burst Pressure at 23°C**		Rolls Delivery		Materials Type
(mm)	(in)	(mm)	(in)		(bars)	(PSI)	(bars)	(PSI)	(m)	(in)	
7	0.28	13.2	0.52	60	7	101	30	435	25	984	Airbus approved, 60 Sh A
7	0.28	13.2	0.52	70	8.5	123	34	493	25	984	Saint-Gobain material, 70 SH A

*: ratio Burst/Operating pressure according ISO 7751:2016

**: tests performed according ISO 1402:2009

Saint-Gobain internal testing showed a decrease of 20% of the burst pressure when used at 200°C

Available Options

Tygon® XLCOMP 60 IB tubing is available in custom sizes, lengths, lay lines, and durometers.

The values listed for working and burst pressures are derived from tests conducted under controlled laboratory conditions. Many factors will reduce the tubing's ability to withstand pressures, including temperature, chemical attack, stress, pulsation and the attachment to fittings. It is imperative that the user conduct tests simulating the conditions of the application prior to specifying the tubing for use.

TYGON® XLCOMP 60 IB TUBING IS NOT INTENDED FOR USE AS AN IMPLANT MATERIAL.



Saint-Gobain Performance Plastics

5 rue du Dauphiné
38070 Saint-Quentin Fallavier
France

Tel.: +334 74 94 82 22
Email: SLS@saint-gobain.com

www.processsystems.saint-gobain.com

NOTE: The data and details given in this document are correct and up to date. This document is intended to provide information about the product and possible applications. This document is not the product specification and does not provide specific features, nor does it guarantee product performance in specific applications. Saint-Gobain cannot anticipate or control the conditions of the field and for this reason strongly recommends that practical tests are conducted to ensure that the product meets the requirements of a specific application.

Tygon® is a registered trademark.