

TUBING SELECTION GUIDE

Food and Beverage



Food Contact*

Regulatory Information

Product	Materials	Features	Pump Tubing/ Transfer Tubing	Food Contact*									Regulatory Information						Bend Radius	Pump Life	Durometer, Shore A (ASTM D2240)	Opacity	Relative Working Pressure Rating	Working Temperature Range, °F (°C)
				Hot Beverages	Carbonated Drinks	Acidic Foods	Oil-Based or Fatty Foods	Beer <7% Ethanol	Alcohol Beverages >7% Ethanol	Dairy-Based Foods	Frozen Foods and Beverages	Hydration	US FDA 21CFR 170-189	EU Regulation No 10/2011	China GB 4806.6 & GB 9685	Japan PL No. 370 of 1959	NSF-51	NSF-61						
Tygon® A-60-F	Thermoplastic Elastomer	Long-Life, Temperature-Resistant Tubing	Pump Tubing	G	G	E	U	G	U	E	E	G	Yes	No	No	No	Yes	No	Better	Best	61	Opaque	Low	-75 to 275 (-60 to 135)
Tygon® E-65-F	Thermoplastic Elastomer	Taste and Odor Free, Long Life Tubing	Pump Tubing	G	G	E	U	G	E	E	E	E	Yes	Yes	No	No	Yes	No	Best	Best	65	Opaque	Low	-112 to 275 (-80 to 135)
Versilon® SPT-50	Platinum-Cured	Peristaltic Pump, Silicone Tubing	Pump Tubing	G	G	E	G	U	U	G	G	G	No	In Progress	No	No	Yes	No	Better	Better	50	Translucent	Low	-112 to 400 (-80 to 204)
Versilon® SPT-50 TF	Platinum-Cured	Peristaltic Pump, Silicone Tubing	Pump Tubing	E	G	G	G	U	U	G	G	G	No	In Progress	No	No	Yes	No	Better	Better	50	Translucent	Low	-112 to 400 (-80 to 204)
Versilon® SPX-60 FB	Peroxide-Cured	Silicone Tubing for Food and Beverage Applications	Pump Tubing	E	G	G	E	U	U	E	G	G	No	Yes	No	No	Yes	No	Better	Good	60	Translucent	Low	-112 to 400 (-80 to 204)
Tygon S3™ B-44-3	Bio-Based Thermoplastic Elastomer	Flexible Tubing for Beverage Transfer	Transfer Tubing	U	E	G	U	G	U	G	U	E	Yes	Yes	No	Yes	Yes	Yes	Best	Better	66	Transparent	Medium	-49 to 165 (-45 to 74)
Tygon S3™ B-44-4X	Bio-Based Thermoplastic Elastomer	Food & Beverage Dispensing Tubing	Transfer Tubing	U	G	G	U	E	U	E	U	G	Yes	Yes	No	Yes	Yes	Yes	Best	Better	66	Transparent	Medium	-49 to 165 (-45 to 74)
Versilon® 2810	Fluoropolymer	Abrasion-Resistant, Flexible Tubing	Transfer Tubing	E	G	E	G	G	E	G	G	G	No	No	No	No	Yes	No	Good	N/A	D65	Opaque	High	250 Maximum (121 Maximum)
Tygon S3™ B-44-5X IB	Bio-Based Thermoplastic Elastomer	Reinforced Pressure Tubing for Cold Beverage Dispensing	Transfer Tubing	U	E	G	U	G	U	E	E	G	Yes	Yes	No	No	Yes	Yes	Good	N/A	66	Transparent-Braided	High	-32 to 165 (-36 to 74)
Tygon® A-60-F IB	Thermoplastic Elastomer	Flexible, Temperature & Pressure-Resistant Tubing	Transfer Tubing	G	G	G	U	G	U	E	E	G	Yes	No	No	No	Yes	No	Good	N/A	61	Opaque	High	-75 to 275 (-60 to 135)
Tygon® HA-1000	Polyolefin	Chemical Resistant Food and Beverage Dispensing Tubing	Transfer Tubing	U	G	E	U	G	E	G	U	G	Yes	Yes	No	No	Yes	No	Best	N/A	75	Translucent	Medium	-103 to 130 (-75 to 54)
Versilon® PFA-F	Fluoropolymer	High Purity, Flexible Tubing	Transfer Tubing	E	G	G	G	G	E	G	G	G	Yes	Yes	No	No	No	No	Better	N/A	D60	Translucent	High	-320 to 500 (-196 to 260)
Versilon® SPT-70 FB IB	Platinum-Cured	Reinforced, Flexible Silicone Tubing	Transfer Tubing	G	G	G	E	U	U	E	G	G	Yes	Yes	Yes	No	Yes	No	Good	N/A	70	Translucent-Braided	High	-112 to 400 (-80 to 204)
Versilon® C-210-A	Thermoplastic Elastomer	Clear, Multipurpose Oil Transfer Tubing	Transfer Tubing	U	G	U	E	U	U	G	G	U	Yes	No	No	No	No	No	Best	N/A	82	Transparent	Medium	-100 to 175 (-74 to 79)
Versilon® Silver	Bio-Based Thermoplastic Elastomer	Phthalate-Free, Fluid Transfer Tubing	Transfer Tubing	U	G	G	U	G	G	G	U	E	No	No	No	No	Yes	No	Better	N/A	69	Opaque	Medium	-31 to 165 (-35 to 74)
Versilon® FEP-F	Fluoropolymer	Clear, High-Temperature Flexible Tubing	Transfer Tubing	E	G	G	G	G	G	G	G	G	Yes	Yes	No	No	No	No	Better	N/A	D55	Transparent	High	-100 to 400 (-73 to 204)
Tygon® E-70-V-CE	Bio-Based Thermoplastic Elastomer	Flexible, Taste Barrier Tubing	Transfer Tubing	U	G	G	U	G	E	G	U	E	No	No	No	No	Yes	No	Better	N/A	72	Translucent	Medium	-47 to 160 (-44 to 71)
Versilon® C-544-A	Thermoplastic Elastomer	Multi-Purpose, Abrasion Resistant Tubing	Transfer Tubing	U	G	U	E	U	U	G	G	G	Yes	No	No	No	No	No	Best	N/A	85	Transparent	Medium	-100 to 180 (-74 to 82)

*Food Contact Ratings: E Excellent
G Good
U Unsatisfactory

